

Technical Bulletin # 3114

### Product Description

**INSULCAST 987 CM** is a semi-flexible, potting compound that exhibits excellent electrical and physical properties over a wide range of temperatures.

### Properties Uncured

	<u>Part A</u>	<u>Part B</u>	
COLOR:	Neutral	Neutral	
VISCOSITY, cps @ 23°C:	80,000	50,000	ASTM D 2393
SPECIFIC GRAVITY:	1.41	1.37	
MIX RATIO (by wt.) A to B:		2 to 3	
MIXED VISCOSITY:		60,000	ASTM D 2393
WORK LIFE @ 25°C, hours:		>48	
SHELF LIFE @ 25°C, months:		12	

### Properties Cured

#### PHYSICAL

HARDNESS, DUROMETER (Shore D):	65		ASTM D 2240
COEFFICIENT OF THERMAL EXPANSION, °C:	45 x 10 <sup>-6</sup>		
THERMAL CONDUCTIVITY, BTU-in/(ft <sup>2</sup> )(hr)(°F):	2.9		
SERVICE TEMPERATURE, °C:	-55 to 155		

### Electrical

DIELECTRIC STRENGTH, volts/mil:	375		ASTM D 149
DIELECTRIC CONSTANT, 1 KHz:	4.9		ASTM D 150
DISSIPATION FACTOR, 1 KHz:	0.05		ASTM D 150
VOLUME RESISTIVITY, ohm-cm:	1 x 10 <sup>14</sup>		ASTM D 257

## Mixing Instructions

1. Pre-mix both components in their original containers to insure consistency.
2. Pre-heat both components to 50° - 60°C, to lower viscosity for ease of mixing.
3. Measure out 2 parts of **Insulcast 987 CM** Part A to 3 parts of Part B (by weight).
4. Mix thoroughly, scraping the sides and bottom of container.
5. Evacuate @ 29 in. Hg for void-free casting.
6. Pour into unit or cavity.

## Cure Schedule

2 hours @ 120°C or 24 hours @ 75°C

**Date** 02/2009

### **IMPORTANT:**

The following supersedes any provision in your company's forms, letters and papers. ITW POLYMER TECHNOLOGIES makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW POLYMER TECHNOLOGIES BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW POLYMER TECHNOLOGIES for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW POLYMER TECHNOLOGIES sole opinion, to justify such refund.

### **HEALTH CAUTION:**

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

**PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.**