

Self-Extinguishing Epoxy Compound
Flame Class 94 V-0

Technical Bulletin # 3023

Product Description

INSULCAST 333 is a moderate viscosity, self-extinguishing, epoxy potting/casting compound which conforms to the component program of Underwriters Laboratories' Flame Class 94V-O.

Properties Uncured

	INSULCAST 333	INSULCURE 9	INSULCURE 44	
COLOR, VISUAL:	Black	Amber	Amber	
VISCOSITY @ 25°C, cps:	13,000	55	10	ASTM D 2393
SPECIFIC GRAVITY:	1.55	0.97	1.00	
MIX RATIO (by wt.):	100	:6	:14	
MIXED VISCOSITY, cps:		2,000	1,500	ASTM D 2393
POT LIFE (100g.) @ 25°C, hrs:		1	1	
SHELF LIFE @ 25°C, months:	12	12	12	

Properties Cured**PHYSICAL**

HARDNESS, DUROMETER (Shore D):		85	85	ASTM D 2240
TENSILE STRENGTH, psi:		11,500	12,000	ASTM D 638
TENSILE ELONGATION, %:		2.75	3.75	ASTM D 638
FLEXURAL STRENGTH, psi:		17,500	19,500	ASTM D 790
COMPRESSIVE STRENGTH, psi:		14,000	14,500	ASTM D 695
COEFFICIENT OF THERMAL EXPANSION, °C:		48 x 10 ⁻⁶	48 x 10 ⁻⁶	
FLAMMABILITY RATING U.L.:		Pass	Pass	
THERMAL CONDUCTIVITY, BTU-in/(ft ²)(hr)(°F):		4.3	4.2	
HEAT DISTORTION POINT, °C:		80	75	
SERVICE TEMPERATURE, °C:		105	105	

Electrical

DIELECTRIC STRENGTH, volts/mil:		410	430	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz:		4.4	4.5	ASTM D 150
DISSIPATION FACTOR, 1 KHz:		0.02	0.02	ASTM D 150
VOLUME RESISTIVITY, ohm-cm:		1 x 10 ¹⁵	1 x 10 ¹⁵	ASTM D 257

Use Instructions

1. Premix **INSULCAST 333** in original container being certain to reincorporate any fillers that may have settled.
2. Weigh out required amount of **INSULCAST 333**.
3. Weigh into **INSULCAST 333**, the proper amount of curing agent according to the ratios indicated.
4. Mix thoroughly, being careful to scrape sides and bottom of container to ensure proper blending.
5. Evacuate for 2-5 minutes if void-free castings are required.
6. Pour into cavity or mold.

Cure Schedule

Insulcure 9: 8-12 hours at room temperature (25°) or 2 hours at 50°C.

Insulcure 44: 2 hours at 100°C, (212°F) for masses less than 1/2 lb.
For masses above 1/2 lb. cure 2 hours at 80°C, (177°F) plus 2 hours at 100°C (212°F).
For optimum high temperature properties, post cure 1 hour at 150°C (302°F).

Storage Requirements

This product has a tendency to settle upon shipment or storage. The product should be re-mixed well prior to use. Store material in a cool dry place.

Date 08/2006

IMPORTANT:

The following supersedes any provision in your company's forms, letters and papers. ITW POLYMER TECHNOLOGIES makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW POLYMER TECHNOLOGIES BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW POLYMER TECHNOLOGIES for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW POLYMER TECHNOLOGIES sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.