

Semi-Flexible Flame Retardant Epoxy Compound with Superior Thermal Shock Resistance

Technical Bulletin # 3040

Product Description

INSULCAST 985 FR is a semi-flexible flame retardant epoxy compound displaying the best thermal shock resistance currently available in an epoxy compound. It has excellent electrical properties over a wide range of temperatures and conforms to the component program of Underwriters Laboratories' Flame Class 94V-O. **INSULCAST 985 FR** makes use of the latest polymer and filler technology.

Properties Uncured

	<u>Part A</u>	<u>Part B</u>	
COLOR, VISUAL:	Black	Neutral	
VISCOSITY, cps:	18,000	80,000	ASTM D 2393
SPECIFIC GRAVITY- nominal:	1.62	1.50	
MIX RATIO (by weight):		1:1	
MIXED VISCOSITY, cps @ 25°C:		50,000	ASTM D 2393
POT LIFE @ 25°C, hours:		4-6	
SHELF LIFE @ 25°C, months:		12	

Properties Cured

PHYSICAL

HARDNESS, DUROMETER (Shore D):	70	ASTM D 2240
THERMAL SHOCK, Method 107E:	Passes B-1	MIL STD 202
FLAMMABILITY RATING-UL 94V0	Passes	
COEFFICIENT OF THERMAL EXPANSION, °C:	32×10^{-6}	
THERMAL CONDUCTIVITY, BTU-in/(ft ²)(hr)(°F):	3.5 ± 0.5	
SERVICE TEMPERATURE, °C:	-55 to 155	

Electrical

DIELECTRIC STRENGTH, volts/mil:	425	ASTM D 149
DIELECTRIC CONSTANT, 1 KHz:	3.8	ASTM D 150
DISSIPATION FACTOR, 1 KHz:	0.03	ASTM D 150
VOLUME RESISTIVITY, ohm-cm:	6×10^{15}	ASTM D 257

ITW POLYMER TECHNOLOGIES

130 Commerce Drive • Montgomeryville, PA 18936 • 215-855-8450 • Fax 215-855-4688 • www.insulcast.com

Mixing Instructions

1. Pre-mix both components in their original containers to insure consistency.
2. Pre-heat both components to 50° - 60°C, to lower viscosity for ease of mixing.
3. Measure out equal parts (by weight) of both components.
4. Mix thoroughly, scraping the sides and bottom of container.
5. Evacuate @29 in. Hg for void-free casting.
6. Pour into unit or cavity.

Cure Schedule

16 hours @ 85°C OR 2 hours @ 125°C

Date 08/2006

IMPORTANT:

The following supersedes any provision in your company's forms, letters and papers. ITW POLYMER TECHNOLOGIES makes NO WARRANTY, WHETHER EXPRESSED OR IMPLIED, INCLUDING WARRANTIES OF MERCHANTABILITY OR OF FITNESS FOR A PARTICULAR PURPOSE FOR THIS PRODUCT. No statements or recommendations contained in the product literature are to be construed as inducements to infringe any relevant patent, now or thereafter in existence. UNDER NO CIRCUMSTANCES SHALL ITW POLYMER TECHNOLOGIES BE LIABLE FOR INCIDENTAL, CONSEQUENTIAL OR OTHER DAMAGES FROM ALLEGED NEGLIGENCE, BREACH OF WARRANTY, STRICT LIABILITY OR ANY OTHER THEORY, ARISING OUT OF THE USE OR HANDLING OF THIS PRODUCT. The sole liability of ITW POLYMER TECHNOLOGIES for any claims arising out of the manufacture, use or sale of its products shall be to refund the buyer's purchase price, provided such products have been demonstrated in ITW POLYMER TECHNOLOGIES sole opinion, to justify such refund.

HEALTH CAUTION:

Avoid breathing possible fumes, mists and vapors which can cause severe respiratory damage. Use of NIOSH approved breathing apparatus is required for more than minimal exposure. Always work in areas with adequate ventilation to allow dissipation of polyamine and other chemical fumes, and where applicable, solvent fumes. Use of goggles, protective garments, rubber gloves, protective cream is required. If material gets into eyes, flush thoroughly with clean water for twenty (20) minutes; then seek medical treatment. Avoid skin contact. Material can cause contact dermatitis. Always wash exposed areas immediately, using warm water and soap, followed by rinsing with clean water. Observe all safety precautions. It is important when using solvent based materials or solvents to keep away from open flame or ignition source.

PLEASE REFER TO MATERIAL SAFETY DATA SHEET FOR FURTHER FIRST AID INFORMATION. FOR CHEMICAL EMERGENCY, CALL CHEMTREC (DAY OR NIGHT) 800 424-9300.